

日本磁気学会

ISSN 2432-0250

Journal of the Magnetics Society of Japan

Electronic Journal URL: <https://www.jstage.jst.go.jp/browse/msjmag>

Vol.47 No.6 2023

Journal

Thin Films, Fine Particles, Multilayers, Superlattices

Magneto-Optical Spectroscopy of Epitaxial $\text{Co}_x\text{Fe}_{3-x}\text{O}_4$ (001) Thin Films

S. Wang, H. Onoda, J. Harbovsky, H. Yanagihara, J. Inoue, M. Veis, and T. Ishibashi ...137

JOURNAL OF THE MAGNETICS SOCIETY OF JAPAN

Vol.47 No.6 2023

日本磁気学会

ISSN 2432-0250

HP: <http://www.magnetics.jp/> e-mail: msj@bj.wakwak.com

Electronic Journal: <http://www.jstage.jst.go.jp/browse/msjmag>

Journal of the Magnetism Society of Japan

Vol. 47, No. 6

Electronic Journal URL: <https://www.jstage.jst.go.jp/browse/msjmag>

CONTENTS

Thin Films, Fine Particles, Multilayers, Superlattices

Magneto-Optical Spectroscopy of Epitaxial $\text{Co}_x\text{Fe}_{3-x}\text{O}_4$ (001) Thin Films

..... S. Wang, H. Onoda, J. Harbovsky, H. Yanagihara, J. Inoue, M. Veis, and T. Ishibashi 137

Board of Directors of The Magnetism Society of Japan

President:	Y. Takemura
Vice Presidents:	T. Ono, A. Kikitsu
Directors, General Affairs:	H. Yuasa, T. Yamada
Directors, Treasurer:	A. Yamaguchi, S. Murakami
Directors, Planning:	M. Mizuguchi, Y. Okada
Directors, Editorial:	S. Yabukami, T. Taniyama
Directors, Public Relations:	K. Kakizaki, R. Umetsu
Directors, International Affairs:	H. Kikuchi, Y. Nozaki
Specially Appointed Director, Contents Control & Management:	K. Nakamura
Specially Appointed Director, Societies & Academic Collaborations:	A. Saito
Specially Appointed Director, IcAUMS:	H. Yanagihara
Auditors:	K. Kobayashi, H. Saito



Magneto-optical spectroscopy of epitaxial $\text{Co}_x\text{Fe}_{3-x}\text{O}_4$ (001) thin films

S. Wang, H. Onoda*, J. Harbovsky**, H. Yanagihara*, J. Inoue*, M. Veis**, and T. Ishibashi

Department of Materials Science and Technology, Nagaoka Univ. of Tech., 1603-1 Kamitomioka, Nagaoka 940-2188, Japan

* Department of Applied Physics, Univ. of Tsukuba, 1-1-1 Tennodai, Tsukuba 305-0006, Japan

** Institute of Physics, Charles Univ., Prague 12116, Czech Republic

The magneto-optical (MO) spectra of spinel cobalt ferrite thin films with different distortions were measured in a broad range of 0.59 – 3.54 eV. Instead of using the cation substitution method, we prepared cobalt ferrite thin films with local distortion by using a RF magnetron sputtering method on an Mg_2SnO_4 buffer layer to induce epitaxial strain. We derived the diagonal and off-diagonal elements of the dielectric tensor to investigate the influence of distortion on the MO effect in the films. In the spectra of the off-diagonal dielectric elements, the transitions at 0.8, 1.8, and 2.0 eV, which correspond to the optical transitions of tetrahedral (Co^{2+}) and octahedral [Co^{2+}], [Fe^{3+}], were assigned to crystal field (CF) transitions: (Co^{2+}): ${}^4A_2 \rightarrow {}^4T_1(\text{F})$, ${}^4A_2 \rightarrow {}^4T_1(\text{P})$ and intervalence charge transfer (IVCT) transition: [Co^{2+}] $t_{2g} \rightarrow [\text{Fe}^{3+}] t_{2g}$, respectively. This result revealed that the Co ions were present in both the tetrahedral and octahedral sites in the epitaxial CFO thin films. By comparing the relative amplitude of each MO transition of cobalt ferrite thin films with different distortions, we found that MO spectroscopy is a highly promising tool for evaluating local distortions.

Keywords: magneto-optical spectroscopy, cobalt ferrite, thin films, dielectric tensor, magnetic anisotropy

1. Introduction

Recently, it has been reported that a giant perpendicular magnetic anisotropy (PMA) was induced by a tetragonal distortion in epitaxially grown spinel $\text{Co}_{0.75}\text{Fe}_{2.25}\text{O}_4$ thin films¹⁻⁵. A large PMA energy ($K_u = 1.47 \text{ MJ/m}^3$) of $\text{Co}_{0.75}\text{Fe}_{2.25}\text{O}_4$ thin films grown on a MgO (001) substrate was obtained undergoing 0.7% lattice mismatch². Furthermore, a larger strain was introduced into the $\text{Co}_{0.75}\text{Fe}_{2.25}\text{O}_4$ thin film by introducing Mg_2SnO_4 (MSO) buffer layers with 3.1% lattice mismatch^{5,6}, resulting that a giant PMA energy of 6.1 MJ/m^3 was induced by a large epitaxial strain⁶. This value is much larger than that of the Nd magnet, 4.9 MJ/m^3 ⁷. Understanding the origin of the large magnetic anisotropy (MA) energy is crucial for enhancing the performance of permanent magnets.

The theory predicts that the MA energy of $\text{Co}_x\text{Fe}_{3-x}\text{O}_4$ (CFO) is dependent on the distortion of the octahedral structure in which Co^{2+} ions reside⁸. To investigate the local structure of CFO and its impact on MA, various methods have been utilized, including X-ray magnetic circular dichroism (XMCD), X-ray magnetic linear dichroism (XMLD) spectroscopy, and magneto-optical (MO) spectroscopy. The XMCD and XMLD spectra of epitaxial $\text{Co}_x\text{Fe}_{3-x}\text{O}_4$ ($x=0.2, 0.6$) thin films, prepared by pulsed laser deposition method, revealed that the substantial MA energy originates from the large orbital magnetic moments of distorted octahedron including Co^{2+} ($3d^7$), and no signals of tetrahedral Co^{2+} were detected⁹. In contrast, MO spectroscopy is a convenient method for studying the electronic structure of materials

without the use of a large facility for X-ray source. Numerous studies on MO spectroscopy of spinel CFO have been reported¹⁰⁻²². Unlike most spinel ferrites such as Fe_3O_4 , MgFe_2O_4 , $\text{Li}_{0.5}\text{Fe}_{2.5}\text{O}_4$ and NiFe_2O_4 , the MO spectrum of spinel CFO features distinct transitions in visible region and near-infrared region, due to Co ions in tetrahedral and octahedral sites¹⁵. As a result, the MO spectroscopy has a potential to be utilized to evaluate the local structure of CFO thin films.

Previous studies on MO spectroscopy of ferrites have revealed that the disturbed local symmetry can alter the MO spectrum by the substitution of nonmagnetic cations for Fe ions in spinel Fe_3O_4 ^{22,23} and CoFe_2O_4 ²⁴⁻²⁶. However, substituting other cations affect not only the local symmetry but also the compositions resulting in a change in their magnetic properties, meaning that MO spectra are influenced by more than one factor. In contrast, our study focuses on the effect of distortion on the MO spectroscopy of CFO thin films without changing compositions. To solve these problems, we studied $\text{Co}_{0.75}\text{Fe}_{2.25}\text{O}_4$ thin films with different levels of distortion by introducing an MSO buffer layer on MgO (001) substrate via RF magnetron sputtering. MO spectra of epitaxial spinel-type CFO thin films over a wide energy range (0.59 – 3.54 eV) have been measured for the first time. Dielectric tensor of $\text{Co}_{0.75}\text{Fe}_{2.25}\text{O}_4$ thin films were investigated. Finally, the relationship between local strain and each optical transition was discussed.

2. Dielectric tensor

The Faraday and Kerr spectra of magnetic thin films are dependent on the incident angle and orientation of magnetization, and thus do not represent an intrinsic response. In contrast, the dielectric tensor directly reflects the electronic structure and the transition matrix

Corresponding author: T. Ishibashi (e-mail: t_bashi@mst.nagaokaut.ac.jp).

of optical transitions. For a uniaxial anisotropy with magnetization in the z-direction, the dielectric tensor has the following form,

$$\varepsilon = \begin{pmatrix} \varepsilon_{xx} & -\varepsilon_{xy} & 0 \\ \varepsilon_{xy} & \varepsilon_{xx} & 0 \\ 0 & 0 & \varepsilon_{zz} \end{pmatrix}, \quad (1)$$

where the diagonal element $\varepsilon_{xx} = \varepsilon'_{xx} + i\varepsilon''_{xx}$ and the off-diagonal element $\varepsilon_{xy} = \varepsilon'_{xy} + i\varepsilon''_{xy}$.

The real and imaginary part of ε_{xx} and ε_{xy} can be expressed in terms of refractive index n , the extinction coefficient κ , Faraday rotation θ_F , and Faraday ellipticity η_F as follows²⁷⁾,

$$\varepsilon'_{xx} = n^2 - \kappa^2, \quad (2)$$

$$\varepsilon''_{xx} = 2n\kappa, \quad (3)$$

$$\varepsilon'_{xy} = \frac{\lambda}{\pi\zeta} (n\eta_F - \kappa\theta_F), \quad (4)$$

$$\varepsilon''_{xy} = \frac{\lambda}{\pi\zeta} (n\theta_F + \kappa\eta_F), \quad (5)$$

where λ is a wavelength and ζ is a thickness of a sample.

From equations (4) and (5), we know that the off-diagonal elements relate to the magnetic properties, and the off-diagonal elements can be determined by measuring the Faraday rotation and ellipticity.

In this study, we used the Lorentz functions to decompose the off-diagonal dielectric tensor elements to each transition, where the diamagnetic and paramagnetic transitions were considered²⁸⁾. The expression of diamagnetic transition is described as,

$$\varepsilon(\omega) = A \cdot \frac{2(\omega_0 - \omega) * \Gamma - i((\omega_0 - \omega)^2 - \Gamma^2)}{\omega * ((\omega_0 - \omega)^2 + \Gamma^2)^2}, \quad (6)$$

and the paramagnetic transition is expressed as,

$$\varepsilon(\omega) = A \cdot \frac{2\omega_0\Gamma - i\omega_0(\omega_0^2 - \omega^2 + \Gamma^2)}{(\omega_0^2 - \omega^2 + \Gamma^2)^2 + 4\omega^2\Gamma^2}, \quad (7)$$

where A is transition amplitude, ω_0 is resonance frequency, and Γ is a half width at half maximum.

3. Experiments

3.1 Sample preparation and characterizations

We prepared two CFO samples, one of CFO thin films grown on a MgO (001) substrate, and another CFO thin film grown on an MSO buffer layer on the MgO (001) substrate. CFO thin film with a thickness of 20 nm was prepared on MgO (001) substrates as CFO/MgO by the reactive RF magnetron sputtering technique using CoFe (1:3 atomic ratio) alloy targets. To change the distortion of CFO thin films, an MSO buffer layer of 7 nm thickness were grown on single crystal MgO (001) substrates at 600 °C by the reactive RF magnetron sputtering using Mg and Sn metal targets under 0.5 Pa pressure of Ar and O₂ mix gas. Then the MSO film was post-annealed at 1000 °C for 10 min in air. CFO thin film with a thickness of 20 nm was grown on the post-annealed MSO films and MgO substrate as CFO/MSO/MgO at 500 °C using a CoFe (1:3 atomic ratio) metal alloy, under 0.5 Pa pressure of Ar and O₂ mix gas.

Magnetization curves were measured by a superconducting quantum interference device, SQUID-

VSM (Quantum Design, MPMS), at fields up to ± 9 T. Thicknesses of CFO thin films were determined a spectroscopic ellipsometer (M-2000DI-YK, J.A.Woollam). The crystallinity of prepared CFO thin films was characterized by the X-ray diffractometer (Rigaku, SmartLab) using CuK α_1 radiation ($\lambda = 0.154059$ nm) for out-of-plane measurements and CoK α_1 radiation ($\lambda = 0.178900$ nm) for in-plane measurement monochromized with a double Ge (220) monochromator.

3.2 Measurements of optical and MO properties of CFO thin films

To investigate the complete dielectric tensor, we used an ellipsometer to determine the diagonal element, and the off-diagonal tensor were derived by spectroscopic ellipsometry and MO spectroscopy. The optical properties were measured by spectroscopic ellipsometry for an energy range between 0.73 – 6.02 eV (206 – 1690 nm), RC2 (J.A.Woollam). The diagonal dielectric elements were fitted with the Tauc-Lorentz model using the CompleteEASE (J. A. Woollam Co., Inc.) software. MO spectra ranging from 0.59 – 3.54 eV (350 – 2100 nm) were measured by a multi-channel MO spectrometer²⁹⁾.

The MO spectrometer used in this study was shown in Fig. 1. All optical components of the MO spectrometer were set on an ordinary optical table. The optical setup includes a light source, a pinhole, a polarizer, a quarter-wave plate, an electromagnet (Max filed: ± 1.7 T), an analyzer, a detector, and three collimate lenses. A halogen lamp (U-LH100L-3, TH4-100, Olympus Inc.) with a power of 100 W was used as a light source. A spatial filter was set in front of the light source, with a variable pinhole in the focal point of the two N-BK7 plano-convex lenses L1 and L2 (Transmittance > 80% at 350 – 2100 nm). Two Glan-Thompson prisms with an extinction ratio of 1×10^5 were used as a polarizer and an analyzer. Two types of achromatic quarter-wave plates, SAQWP05M-700 (Thorlabs Inc.) for 325 – 1100 nm and SAQWP05M-1700 (Thorlabs Inc.) for 600 – 2700 nm, were used in the measurement of ellipticity. Two types of multi-channel spectrometers were used. The USB2000+VIS-NIR (Ocean Optics Inc., wavelength range: 350 – 1000 nm) spectrometer with a 2048-element linear silicon CCD array detector (ILX511B, Sony Inc.) was used for the visible light, and the NIRQUEST512-2.5 (Ocean Optics




Fig. 1 Illustration of MO multi-channel spectrometer using Stokes parameter method. *USB2000 + VIS-NIR, NIRQUEST512-2.5 (Ocean Optics Inc.)

Inc., wavelength range: 900 – 2500 nm) with a 512-element InGaAs linear array image sensor (G9208-512W, Hamamatsu Photonics K.K.) was used for the near-infrared light. The transmitted light from the analyzer was focused by the collimation lens L3 into an optical fiber connected to the multi-channel spectrometer. The effective measurement range of the MO spectra is considered between 350 and 2100 nm (3.54 – 0.59 eV) according to the above configurations.

In the process of MO measurement, the polarization axis of the polarizer was fixed to the vertical plane as 0° all the time, and the analyzer and the quarter wave-plate are rotated by a stepping motor (DS102, Suruga Seiki). The magnetic field was applied perpendicular to the sample up to 1.7 T by a double-yoked electromagnet.

To measure the Faraday rotation and Faraday ellipticity spectra, we measured Stokes parameters, defined by azimuth angle θ and ellipticity η as described by

$$\begin{pmatrix} s_0 \\ s_1 \\ s_2 \\ s_3 \end{pmatrix} = \begin{pmatrix} 1 \\ \cos 2\eta \cos 2\theta \\ \cos 2\eta \sin 2\theta \\ \sin 2\eta \end{pmatrix}. \quad (8)$$

In this case, azimuth θ can be expressed as an equation,

$$\theta = \frac{1}{2} \tan^{-1} \left(\frac{s_2}{s_1} \right) = \frac{1}{2} \tan^{-1} \left(\frac{I_{45^\circ} - I_{135^\circ}}{I_{0^\circ} - I_{90^\circ}} \right), \quad (9)$$

where I_{0° , I_{45° , I_{90° , and I_{135° are optical intensities measured with the analyzer angles of 0°, 45°, 90°, and 135°, respectively. For measuring the Faraday ellipticity spectra, the analyzer is fixed to 0°, and the fast axis of the quarter wave-plate is rotated to -45°, +45° with the polarizer, corresponding to left-handed circular polarization (LCP), and right-handed circular polarization (RCP), respectively. Ellipticity η can be expressed by,

$$\eta = \frac{1}{2} \sin^{-1} \left(\frac{s_3}{s_0} \right) = \frac{1}{2} \sin^{-1} \left(\frac{I_{LCP} - I_{RCP}}{I_{LCP} + I_{RCP}} \right), \quad (10)$$

where I_{LCP} and I_{RCP} are the intensities at the detector obtained with polarization states of LCP, and RCP.

Using the above method and a multi-channel spectrometer, Faraday rotation and Faraday ellipticity spectra can be acquired within a mere 5 minutes. To ensure accuracy, all Faraday spectra are averaged in opposite magnetic field directions and calibrated^{29),30)}, effectively removing any offset due to the optical setup. The measurement of Faraday rotation and ellipticity spectra was conducted at room temperature.

4. Results and discussion

X-ray diffraction (XRD) patterns of CFO/MgO and CFO/MSO/MgO measured in both in-plane and out-of-plane orientations are shown in Fig. 2. In Fig. 2 (a), diffraction peaks observed at $2\theta = 95.20^\circ$ for CFO/MgO and 95.59° for CFO/MSO/MgO correspond to the 008 diffractions of CFO with the spinel-type structure with $c = 0.8345$ and 0.8319 nm, respectively. In-plane lattice constants of CFO thin films are determined from CFO (220) diffractions in Fig. 2 (b) to be $a = 0.8425$ nm for CFO/MgO and $a = 0.8439$ nm for CFO/MSO/MgO.

Compared to the lattice constant of bulk CFO ($a = 0.838$ nm), out-of-plane compressive strains of CFO thin films in CFO/MgO and CFO/MSO/MgO were determined to be $\varepsilon_{\perp} = -0.418\%$ and $\varepsilon_{\perp} = -0.728\%$, while in-plane tensile strains were $\varepsilon_{\parallel} = 0.537\%$ and $\varepsilon_{\parallel} = 0.704\%$ for CFO/MgO and CFO/MSO/MgO, respectively. These values are comparable to those reported previously^{2),5)}. The total distortions χ of CFO thin films were defined as $\chi = \varepsilon_{\parallel} - \varepsilon_{\perp}$ ⁶⁾, 0.955% and 1.432% for CFO/MgO and CFO/MSO/MgO. These results indicated that both CFO thin films are distorted by the lattice mismatch. The larger distortion in CFO/MSO/MgO was induced by the MSO buffer layer with larger lattice constant compared to the MgO substrate. Additionally, Laue oscillation was observed in the XRD pattern for the CFO/MgO sample shown in Fig. 2 (a), indicating excellent crystallinity and a smooth surface of CFO thin films. Postannealed MSO layer was investigated by reflection high-energy electron diffraction (RHEED) and cross-sectional transmission electron microscopy (TEM) previously, indicating that MSO layer is single crystal with a flat surface⁶⁾.

Fig. 3 shows magnetization curves of CFO thin films, which were measured with magnetic fields applied perpendicular to the plane. The saturation magnetization (M_s) was measured to be 395 kA/m for both CFO/MgO and CFO/MSO/MgO thin films, which




Fig. 2 XRD patterns of CFO/MgO and CFO/MSO/MgO. (a) Out-of-plane patterns in range of 85 – 100°, (b) In-plane patterns in range of 30 – 40°.




Fig. 3 Out-of-plane hysteresis loop of CFO thin films prepared on MgO and MSO/MgO substrates, measured by SQUID magnetometry.




Fig. 4 Diagonal elements of dielectric tensor of CFO thin films on MgO and MSO/MgO.

was close to that of bulk CFO crystal, 425 kA/m²). The fact that the CFO thin films have M_s comparable to that of bulk CFO crystal suggests that the distortion has not significantly affected the saturation magnetization. On the other hand, the CFO/MgO and CFO/MSO/MgO thin films exhibited different coercive fields of 5.94 A/m and 12.63 A/m, respectively, depending on the distortion. These characteristics of these CFO thin films used in this study is consistent with previous reports^{5),6)}.

The diagonal elements of dielectric tensor ϵ'_{xx} and ϵ''_{xx} of CFO thin films are shown in Fig. 4. Five oscillators were considered to fit the imaginary part of diagonal elements of the dielectric tensor of these CFO thin films, where the parameters used for the fitting are listed in Table 1. Thicknesses of the CFO thin films were determined to be 25.27 ± 0.03 nm for CFO/MgO and 22.47 ± 0.09 nm for CFO/MSO/MgO, respectively. Thicknesses of the MSO buffer layer was determined to be 7.00 ± 0.39 nm. Postannealed MSO layer was also investigated, resulting in a roughness of 1.05 nm, which indicates that

Table 1 Parameters used to fit diagonal elements ϵ''_{xx} of CFO thin films on MgO and MSO/MgO. Lists are peak position ω_0 (eV), full width at half maximum Γ (eV), amplitude A of each oscillator (Osc.).

Sample		Osc. 1	Osc. 2	Osc. 3	Osc. 4	Osc. 5
CFO/ MgO	ω_0	2.17	3.24	3.71	5.53	9.04
	Γ	1.97	0.59	1.53	3.23	0.0001
	A	15.509	1.495	9.403	21.694	11.468
CFO/ MSO/ MgO	ω_0	2.25	3.21	3.69	5.51	7.78
	Γ	1.96	0.64	1.50	3.28	0.41
	A	16.327	1.933	9.038	21.613	3.859

the MSO has a flat surface. The fitting was carried out with small mean squared error (MSE) of 1.669 for CFO/MgO and 2.025 for CFO/MSO/MgO. The real part of diagonal elements ϵ'_{xx} of CFO thin films showed a broad structure with two dominant peaks at 1.9 and 3.0 eV. The imaginary part of diagonal elements ϵ''_{xx} showed that a broad absorption from 1.3 eV. It was found that the ϵ'_{xx} of CFO/MgO is lower than that of CFO/MSO/MgO between 0.73 and 3.1 eV. For ϵ''_{xx} , the intensity of CFO/MSO/MgO is larger than that of CFO/MgO between 1.5 – 4.5 eV. These differences can be attributed to the enhancement of optical absorption caused by the increased distortion of CFO thin films.

Fig. 5 shows the Faraday rotation and ellipticity spectra of the CFO thin films in range of 0.59 to 3.54 eV. Faraday spectra of MgO (001) substrate and MSO buffer layer measured under the same magnetic field were subtracted from the measured spectra to eliminate the influence of the Faraday effect. As the applied magnetic field cannot fully saturate both samples in these measurements, the MO spectra with fully saturated were estimated. Using the magnetic hysteresis loop, the estimated MO spectra were obtained by multiplying coefficients of 1.53 and 2.16 for CFO/MgO and CFO/MSO/MgO, respectively, where those coefficients were obtained by a ratio of a magnetization measured at 1.7 T and a saturation magnetization.

The Faraday spectra are in good agreement with those of the bulk spinel CoFe_2O_4 ^{10),14)}. Both CFO thin films exhibited a broad intense negative peak between 1.3 and 2.8 eV and a narrow dispersion-type transition at 0.8 eV. Although the transition energies did not change, the intensity of the rotation and ellipticity spectra increases significantly in the CFO/MSO/MgO. To understand the microscopic origin of the MO effect, we have derived the off-diagonal elements ϵ_{xy} of the dielectric tensor using equations (4) and (5).

Fig. 6 shows the spectra of real part and imaginary part of ϵ_{xy} of the CFO thin films in the region between 0.73 and 3.54 eV. The structures of ϵ_{xy} of CFO thin films are in good agreement with the previous MO study on bulk CFO crystals¹⁰⁾. To evaluate each optical transition, we fitted the real part of the off-diagonal dielectric tensor element ϵ'_{xy} using equations (6) and (7).




Fig. 5 Faraday rotation θ_F and ellipticity η_F spectra of CFO/MgO and CFO/MSO/MgO.




Fig. 6 Off-diagonal elements of dielectric tensor of CFO thin films on CFO/MgO and CFO/MSO/MgO.

The assignment of MO transitions was based on previous MO spectroscopic studies of CFO^{10,15,22}. The fitting results are presented in Fig. 7. The fitting parameters, including the transition amplitude A , peak position ω_0 (eV), and half width at half maximum Γ (eV), are summarized in Table 2. Five MO transitions at 0.80, 1.32, 1.76, 2.05, and 2.50 eV were considered for both two CFO thin films.

The MO spectra exhibited a diamagnetic transition characterized by two peaks of opposite sign at 0.80 eV in the low photon energy region, as well as a paramagnetic transition featuring a single negative peak at 1.76 eV. These transitions are similar to those reported in Ref.³¹, where optical transitions were found at 0.86 and 1.98 eV corresponded to two types of crystal-field (CF) transitions of tetrahedral Co^{2+} : ${}^4A_2 \rightarrow {}^4T_1(\text{F})$ and ${}^4A_2 \rightarrow {}^4T_1(\text{P})$ in Co-doped ZnO single crystals. Therefore, we assigned the diamagnetic transitions at 0.80 eV to the CF transition of Co^{2+} : ${}^4A_2 \rightarrow {}^4T_1(\text{F})$, and the paramagnetic transition at 1.76 eV was assigned to the CF transition of Co^{2+} : ${}^4A_2 \rightarrow {}^4T_1(\text{P})$. An intense broad paramagnetic transition at 2.05 eV is assigned to an IVCT transition: $[\text{Co}^{2+}]t_{2g} \rightarrow [\text{Fe}^{3+}]t_{2g}$, as identified by Peeters and Martens in polycrystalline bulk CFO¹³. A weak diamagnetic transition is observed





Fig. 7 Fitting to real part of off-diagonal dielectric tensor elements of CFO thin films. (a) CFO/MgO, (b) CFO/MSO/MgO.

at 2.50 eV with two opposite peaks, consistent with a previously reported transition at 2.6 eV in bulk spinel Fe_3O_4 ²³, and assigned to an ISCT transition: $(\text{Fe}^{3+})t_2 \rightarrow [\text{Fe}^{2+}]t_{2g}$. Additionally, our fitting results obtained a broad paramagnetic transition at 1.32 eV with a positive peak, which has not been previously discussed in CFO. However, the exact assignment of this transition cannot be confirmed in this study. It might be related to a CF transition of tetrahedral Co^{3+} : ${}^5E \rightarrow {}^5T_2$, as reported in $(\text{YGd})_3(\text{Co}_x\text{Fe}_{5-x})\text{O}_{12}$ thin films at 0.95 eV^{32,33}, but further investigation is needed to confirm this transition in CFO.

The IVCT transition of $[\text{Co}^{2+}]t_{2g} \rightarrow [\text{Fe}^{3+}]t_{2g}$ and the CF transitions of (Co^{2+}) : ${}^4A_2 \rightarrow {}^4T_1(\text{F})$ and ${}^4A_2 \rightarrow {}^4T_1(\text{P})$ associated with octahedral and tetrahedral sites were observed in both samples, as previously assigned. This result suggests that Co^{2+} is not only present in the octahedral site but also in the tetrahedral site. Previous studies have indicated that the Co cations only exist in the octahedral sites for epitaxial CFO thin films^{6,9}. However, our finding demonstrates that the epitaxial $\text{Co}_{0.75}\text{Fe}_{2.25}\text{O}_4$ thin film is not a complete inverse-spinel structure, despite having a lower Co composition than CoFe_2O_4 . Previous interpretations of the MA in epitaxial CFO as originating solely from the large orbital magnetic

Table 2 Optical transitions of CFO thin films on CFO/MgO and CFO/MSO/MgO between 0.73 and 3.54 eV. Lists are peak position ω_0 (eV), half width at half maximum Γ (eV), amplitude A , and assignment of each transition. Tetrahedral and octahedral sites are denoted by () and [], respectively.

Type		CF	CF	CF	IVCT	ISCT
Assignment		(Co ²⁺): ${}^4A_2 \rightarrow {}^4T_1(F)$	(Co ³⁺): ${}^5E \rightarrow {}^5T_2$	(Co ²⁺): ${}^4A_2 \rightarrow {}^4T_1(P)$	[Co ²⁺] t_{2g} $\rightarrow [Fe^{3+}]t_{2g}$	(Fe ³⁺) t_2 $\rightarrow [Fe^{2+}]t_{2g}$
Shape		dia	para	para	para	dia
CFO/MgO	ω_0	0.80	1.32	1.76	2.05	2.50
	Γ	0.11	0.35	0.10	0.35	0.18
	A	0.0010	0.0342	-0.0280	-0.2550	-0.0009
CFO/MSO/MgO	ω_0	0.80	1.32	1.76	2.05	2.50
	Γ	0.11	0.35	0.10	0.35	0.20
	A	0.0019	0.0624	-0.0473	-0.4463	-0.0020

moment of the octahedral Co²⁺ due to epitaxial strain^{9),34)}, ignoring the effect of tetrahedral Co²⁺. However, we have found that Co²⁺ is also present in tetrahedral site in epitaxial CFO thin films, suggesting that the origin of PMA in epitaxial CFO thin films needs to be re-evaluated.

Compared to the MO spectra of these two CFO thin films, we noticed a significant increase in the transition amplitude of all MO transitions in CFO/MSO/MgO. The IVCT transition [Co²⁺] $t_{2g} \rightarrow [Fe^{3+}]t_{2g}$ amplitude increased 1.75 times from -0.2550 in CFO/MgO to -0.4463 in CFO/MSO/MgO. Similarly, the transition amplitude of the CF transition (Co²⁺): ${}^4A_2 \rightarrow {}^4T_1(F)$ at 0.86 eV increased 1.90 times from -0.0010 in CFO/MgO to -0.0019 in CFO/MSO/MgO. We attribute the alteration of the IVCT transition to the octahedral symmetry perturbation caused by the epitaxial tensile strain. This perturbation increases the distance between [Fe³⁺] and [Co²⁺] for adjacent octahedral sites along the a-axis. As the oscillator strength of the IVCT transition is sensitive to changes in the lattice, the longer lattice constant of the CFO leads to a decrease in the transition amplitude of the IVCT transition [Co²⁺] $t_{2g} \rightarrow [Fe^{3+}]t_{2g}$, as reported by Fontijn et al.²³⁾.

Additionally, an increase in the CF transition (Co²⁺): ${}^4A_2 \rightarrow {}^4T_1(F)$ at 0.86 eV in CFO/MSO/MgO was observed, with an amplitude 1.75 times higher than that of tetrahedral Co²⁺ in CFO/MgO. We considered that this increase is attributed to the perturbation of the tetrahedral symmetry caused by the epitaxial tensile strain, which affects not only the octahedral symmetry but also the trigonal symmetry of the tetrahedral structure²³⁾. Calculation results have shown that the Co L₂₃-edge absorption in the tetrahedral symmetry increases with the increasing crystal field³⁵⁾, which is consistent with our results. Our findings suggest that the distorted tetrahedral symmetry in CFO thin films enhances the tetrahedral CF transitions.

Finally, we compared the intensity ratios of the octahedral transition ([Co²⁺] $t_{2g} \rightarrow [Fe^{3+}]t_{2g}$) to the

tetrahedral transition ((Co²⁺): ${}^4A_2 \rightarrow {}^4T_1(F)$) in CFO/MgO and CFO/MSO/MgO. The ratio was found to be 1 : 0.34 for CFO/MgO and 1 : 0.37 for CFO/MSO/MgO. The slight difference in ratio may be explained by the different cation distributions caused by the distortion. Frisch et al.³⁶⁾ reported that the epitaxial tensile strain reduces inversion, which shift Co from the octahedral site to the tetrahedral site. This shift results in an increase in the tetrahedral transition compared to the octahedral transition. Therefore, the enhanced tetrahedral transition intensity in CFO/MSO/MgO is consistent with the cation distribution changes induced by epitaxial tensile strain as reported by Frisch et al.³⁶⁾. However, further research is necessary to quantitatively evaluate the composition of CFO.

5. Conclusion

We investigated two types of high-quality spinel-type CFO thin films prepared on MgO and MSO/MgO substrates by the RF magnetron sputtering method, which had different strains of 0.955% and 1.432%, respectively, induced by lattice mismatching. Dielectric tensors of those CFO thin films were deduced from the optical and Faraday spectra. By observing MO transitions of tetrahedral (Co²⁺) and octahedral [Co²⁺] in both samples, we revealed that Co ions are present in both tetrahedral and octahedral sites in the epitaxial CFO thin films. Furthermore, comparison of the amplitude of each transition indicated that the induced tensile strain leads to an enhancement of MO transitions in CFO thin films. Our results suggest that the MO spectroscopy serves as a sensitive tool for qualitatively investigating cation distribution in CFO thin films, demonstrating the potential for qualitative evaluation of local strain and laying the groundwork for future quantitative analyses of local strain in CFO thin films.

Acknowledgements The authors acknowledge funding from the Japan Science and Technology Agency (JST)

under Collaborative Research Based on Industrial Demand “High-Performance Magnets: Toward Innovative Development of Next-Generation Magnets” under Grant JPMJSK1415. We also thank Prof. Asada and Dr. Kimura for the measurement of the ellipsometry at the Center for Instrumental Analysis, Yamaguchi University.

References

- 1) A. Lisfi, C. M. Williams, L. T. Nguyen, J. C. Lodder, A. Coleman, H. Corcoran, A. Johnson, P. Chang, A. Kumar, and W. Morgan: *Phys. Rev. B*, **76**, 054405 (2007).
- 2) T. Niizeki, Y. Utsumi, R. Aoyama, H. Yanagihara, J. Inoue, Y. Yamasaki, H. Nakao, K. Koike, and E. Kita: *Appl. Phys. Lett.*, **103**, 162407 (2013).
- 3) H. Yanagihara, Y. Utsumi, T. Niizeki, J. Inoue, and E. Kita: *J. Appl. Phys.*, **115**, 17A719 (2014).
- 4) H. Onoda, H. Sukegawa, E. Kita, and H. Yanagihara: *IEEE Trans. Magn.*, **54**, 2502104 (2018).
- 5) H. Onoda, H. Sukegawa, and H. Yanagihara: *IEEE Trans. Magn.*, **56**, 1 (2020).
- 6) H. Onoda, H. Sukegawa, J. Inoue, and H. Yanagihara: *Adv. Mater. Interfaces*, **8**, 2101034 (2021).
- 7) M. Sagawa, S. Hirose, H. Yamamoto, S. Fujimura, and Y. Matsuura: *Jpn. J. Appl. Phys.*, **26**, 785 (1987).
- 8) J. Inoue, H. Yanagihara, and E. Kita: *Mater. Res. Express*, **1**, 046106 (2014).
- 9) J. Okabayashi, M. A. Tanaka, M. Morishita, H. Yanagihara, and K. Mibu: *Phys. Rev. B*, **105**, 134416 (2022).
- 10) J. W. D. Martens, W. L. Peeters, H. M. van Noort, and M. Erman: *J. Phys. & Chem. Solids*, **46**, 411 (1985).
- 11) N. Evtihiev, N. Economov, A. Krebs, N. Zamjatina, V. Baurin, and V. Pinko: *IEEE Trans. Magn.*, **12**, 773 (1976).
- 12) J. W. D. Martens and A. Voermans: *IEEE Trans. Magn.*, **20**, 1007 (1984).
- 13) W. L. Peeters and J. W. D. Martens: *J. Appl. Phys.*, **53**, 8178 (1982).
- 14) L. Stichauer, G. Gavaille, and Z. Simsa: *J. Appl. Phys.*, **79**, 3645 (1996).
- 15) W. F. J. Fontijn, P. J. van der Zaag, and R. Metselaar: *J. Appl. Phys.*, **83**, 6765 (1998).
- 16) K. J. Kim, M. H. Lee, and S. H. Lee: *J. Appl. Phys.*, **91**, 9974 (2002).
- 17) Y. A. Gromova, V. G. Maslov, M. A. Baranov, R. Serrano-García, V. A. Kuznetsova, F. Purcell-Milton, Y. K. Gun'ko, A. V. Baranov, and A. V. Fedorov: *J. Phys. Chem. C*, **122**, 11491 (2018).
- 18) B. S. Holinsworth, N. C. Harms, S. Fan, D. Mazumdar, A. Gupta, S. A. McGill, and J. L. Musfeldt: *APL Mater.*, **6**, 066110 (2018).
- 19) R. Illa, R. Ješko, R. Silber, O. Životský, K. M. Kutláková, L. Matějová, M. Kolenčík, J. Pištora, and J. Hamrle: *Mater. Res. Bull.*, **117**, 96 (2019).
- 20) J. W. D. Martens: *J. Appl. Phys.*, **59**, 3820 (1986).
- 21) K. Yasuda, M. Nishikawa, and T. Ishibashi: *Jpn. J. Appl. Phys.*, **59**, S3EA01 (2020).
- 22) W. F. J. Fontijn, P. J. van der Zaag, L. F. Feiner, R. Metselaar, and M. A. C. Devillers: *J. Appl. Phys.*, **85**, 5100 (1999).
- 23) W. F. J. Fontijn, P. J. van der Zaag, M. A. C. Devillers, V. A. M. Brabers, and R. Metselaar: *Phys. Rev. B*, **56**, 5432 (1997).
- 24) B. Zhou, Y. Zhang, Y. Yu, C. Liao, C. Yan, L. Chen, and S. Wang: *Phys. Rev. B*, **68**, 024426 (2003).
- 25) B. Zhou, Y. Zhang, C. Liao, F. Cheng, C. Yan, L. Chen, and S. Wang: *Appl. Phys. Lett.*, **79**, 1849 (2001).
- 26) B. Zhou, Y. Zhang, C. Liao, C. Yan, L. Chen, and S. Wang: *Solid State Commun.*, **126**, 593 (2003).
- 27) S. Wittekoek, T. J. A. Popma, J. M. Robertson, and P. F. Bongers: *Phys. Rev. B*, **12**, 2777 (1975).
- 28) J. C. Suits: *IEEE Trans. Magn.*, **8**, 95 (1972).
- 29) S. Wang, M. Nishikawa, T. Ishibashi, and K. Sato: *Jpn. J. Appl. Phys.*, **59**, S3EA02 (2020).
- 30) K. Sato, H. Hongu, H. Ikekame, Y. Tosaka, M. Watanabe, K. Takanashi, and H. Fujimori: *Jpn. J. Appl. Phys.*, **32**, 989 (1993).
- 31) R. Pappalardo, D. L. Wood, and R. C. Linares: *J. Chem. Phys.*, **35**, 2041 (1961).
- 32) T. Saito, K. Tamanoi, K. Shinagawa, and T. Tsushima: *J. Magn. Soc. Jpn.*, **11** (Suppl. No. S1), 245 (1987).
- 33) L. McAven and K. Shinagawa: *J. Phys. Condens. Matter*, **14**, 11859 (2002).
- 34) J. Inoue, H. Onoda, and H. Yanagihara: *J. Phys. D: Appl. Phys.*, **53**, 195003 (2020).
- 35) M. Wu, X. Huang, K. H. L. Zhang, S. Hu, L. Chen, H.-Q. Wang, and J. Kang: *Phys. Rev. B*, **104**, 075109 (2021).
- 36) D. Fritsch and C. Ederer: *Appl. Phys. Lett.*, **99**, 081916 (2011).

Received May 14, 2023; Accepted Jul. 18, 2023

Editorial Committee Members • Paper Committee Members

S. Yabukami and T. Taniyama (Chairperson), N. H. Pham, D. Oyama and M. Ohtake (Secretary)					
H. Aoki	M. Goto	T. Goto	K. Hioki	S. Inui	K. Ito
M. Iwai	Y. Kamihara	H. Kikuchi	T. Kojima	H. Kura	A. Kuwahata
K. Masuda	Y. Nakamura	K. Nishijima	T. Nozaki	T. Sato	E. Shikoh
T. Suetsuna	K. Suzuki	Y. Takamura	K. Tham	T. Tanaka	M. Toko
N. Wakiya	S. Yakata	A. Yao	S. Yamada	M. Yoshida	
N. Adachi	K. Bessho	M. Doi	T. Doi	T. Hasegawa	R. Hashimoto
S. Haku	S. Honda	S. Isogami	T. Kawaguchi	N. Kikuchi	K. Kobayashi
T. Maki	S. Muroga	M. Naoe	T. Narita	Y. Sato	S. Seino
M. Sekino	Y. Shiota	S. Sugahara	I. Tagawa	K. Tajima	M. Takezawa
T. Takura	S. Tamaru	S. Yoshimura			

Notice for Photocopying

If you wish to photocopy any work of this publication, you have to get permission from the following organization to which licensing of copyright clearance is delegated by the copyright owner.

〈All users except those in USA〉

Japan Academic Association for Copyright Clearance, Inc. (JAACC)
6-41 Akasaka 9-chome, Minato-ku, Tokyo 107-0052 Japan
Phone 81-3-3475-5618 FAX 81-3-3475-5619 E-mail: info@jaacc.jp

〈Users in USA〉

Copyright Clearance Center, Inc.
222 Rosewood Drive, Danvers, MA01923 USA
Phone 1-978-750-8400 FAX 1-978-646-8600

If CC BY 4.0 license icon is indicated in the paper, the Magnetics Society of Japan allows anyone to reuse the papers published under the Creative Commons Attribution International License (CC BY 4.0).

Link to the Creative Commons license: <http://creativecommons.org/licenses/by/4.0/>

Legal codes of CC BY 4.0: <http://creativecommons.org/licenses/by/4.0/legalcode>

編集委員・論文委員

藪上 信 (理事)	谷山智康 (理事)	Pham NamHai (幹事)	大竹 充 (幹事)	小山大介 (幹事)					
青木 英恵	伊藤啓太	乾 成里	岩井守生	神原陽一	菊池弘昭	藏 裕彰	桑波田晃弘	小嶋隆幸	
後藤 太一	後藤 穰	佐藤 拓	仕幸英治	末綱倫浩	鈴木和也	高村陽太	田中哲郎	都甲 大	
Kim Kong Tham		仲村泰明	西島健一	野崎友大	日置敬子	増田啓介	八尾 惇	家形 論	
山田晋也	吉田征弘	脇谷尚樹							
安達信泰	磯上慎二	川口昂彦	菊池伸明	小林宏一郎	佐藤佑樹	塩田陽一	菅原 聡	清野智史	
関野正樹	田倉哲也	田河育也	竹澤昌晃	田島克文	田丸慎吾	土井達也	土井正晶	直江正幸	
成田正敬	白 怜士	橋本良介	長谷川 崇	別所和宏	本多周太	榎 智仁	室賀 翔	吉村 哲	

複写をされる方へ

当学会は下記協会に複写複製および転載複製に係る権利委託をしています。当該利用をご希望の方は、学術著作権協会 (<https://www.jaacc.org/>) が提供している複製利用許諾システムもしくは転載許諾システムを通じて申請ください。

権利委託先：一般社団法人学術著作権協会

〒107-0052 東京都港区赤坂9-6-41 乃木坂ビル

電話 (03) 3475-5618 FAX (03) 3475-5619 E-mail: info@jaacc.jp

ただし、クリエイティブ・コモンズ [表示 4.0 国際] (CC BY 4.0) の表示が付されている論文を、そのライセンス条件の範囲内で再利用する場合には、本学会からの許諾を必要としません。

クリエイティブ・コモンズ・ライセンス <http://creativecommons.org/licenses/by/4.0/>

リーガルコード <http://creativecommons.org/licenses/by/4.0/legalcode>

Journal of the Magnetics Society of Japan

Vol. 47 No. 6 (通巻第330号) 2023年11月1日発行

Vol. 47 No. 6 Published Nov. 1, 2023

by the Magnetics Society of Japan

Tokyo YWCA building Rm207, 1-8-11 Kanda surugadai, Chiyoda-ku, Tokyo 101-0062

Tel. +81-3-5281-0106 Fax. +81-3-5281-0107

Printed by JP Corporation Co., Ltd.

Sports Plaza building 401, 2-4-3, Shinkamata Ota-ku, Tokyo 144-0054

Advertising agency: Kagaku Gijutsu-sha

発行：(公社)日本磁気学会 101-0062 東京都千代田区神田駿河台 1-8-11 東京YWCA会館 207 号室

製作：ジェイピーシー 144-0054 東京都大田区新蒲田 2-4-3 スポーツプラザビル401 Tel. (03) 6715-7915

広告取扱い：科学技術社 111-0052 東京都台東区柳橋 2-10-8 武田ビル4F Tel. (03) 5809-1132

Copyright ©2023 by the Magnetics Society of Japan